

Investigation of The Relationship Between The Substituent and Nonlinear Optical Properties in 2- (Phenyl ((4-Vinylphenyl)Amino) Methyl)Phenol Derivative Compounds by DFT Method

Yeliz Ulaş

Bursa Uludag University, Faculty of Art and Science, Department of Chemistry, Bursa, Turkey.
yelizulas@uludag.edu.tr*

(Received on 15th September 2020, accepted in revised form 2nd February 2021)

Summary:In this study, NLO properties and substituent relationship of the recently synthesized three alkylaminophenol compounds, which have electron-donating and electron-withdrawing groups were investigated. The polarizability ($\langle\alpha\rangle$), the anisotropy of the polarizability ($\langle\Delta\alpha\rangle$), groundstate dipole moment (μ) and the first-order hyperpolarizability (β) were studied. HF method and DFT/B3LYP, WB97XD methods with 6-311++ G(d,p) set were used for calculations. p-Nitroaniline was selected as a reference compound. Also, E_{HOMO} (the highest occupied molecular orbital energy), E_{LUMO} (the lowest unoccupied molecular orbital energy), HOMO-LUMO energy gap (ΔE), molecular surface and FMOs analysis were studied.

Keywords: NLO, DFT, Alkylaminophenol.

Introduction

2- (phenyl ((4-vinylphenyl) amino) methyl) phenol compound is one of the alkylaminophenol derivative compounds[1-4]. Generally, Alkylaminophenol compounds are used medical field[5-6]. An aromatic ring and OH group are included in their structure. The presence of the OH group causes these compounds to have antioxidant properties[. In addition, the presence of groups attached to the aromatic ring plays an important role in their chemical activity. These compounds were synthesis very high yields without catalysis with petasis reaction. Although there are many publications about synthesis, structural and electronic properties on alkylaminophenols in the literature[7-14], there are no studies on its optical properties.

The nonlinear optical (NLO) properties of the molecules play an important role in signal processing in communication technology, in the field of optoelectronics and photonics technologies, laser technology, optical memory design[15-19]. Despite the need for materials with these properties, it is difficult to define a new NLO material class. The NLO properties of molecules emerge from delocalized π -electrons that move throughout the molecule. Increased conjugation and incorporation of the donor and acceptor groups in the molecule causes its NLO property to change. Quantum chemical calculations are used to describe the relationship between NLO properties and electronic structure[20-25]. In this study; NLO analysis, thermochemical and electronic properties for alkylaminophenol compounds were investigated.

Since there is no standard compound in the literature where NLO properties of alkylaminophenols can be compared, the data obtained are compared with p-Nitroaniline (pNA). pNA is one of the simplest molecules with an electron donor and acceptor system. Numerous studies have provided information on the photochemical properties of p-nitroaniline[26-28]. This is the reason why it is preferred in this study.

In this study; Gaussian 09W program, which is a very comprehensive program including molecular mechanics, semi-experimental and ab initio methods, was used. Quantum mechanical calculations; It was carried out by the HF and DFT methods. For the first time in the literature, NLO properties and thermodynamic stability of three alkylaminophenol monomers with electron acceptor and donor groups were investigated by the HF and DFT/ B3LYP and WB97XD methods with 6-311 ++ G (d, p) set.

Experimental

Synthesis

Compounds were synthesized in the previous study[29].

Computational Method

Gaussian 09 software package[30] was used for HF and DFT calculations. Gauss-View 5.0 program[31] was used for molecular modelling.

Results and Discussion

*To whom all correspondence should be addressed.

Optimization structure and MEP

The compounds 2-((4-methoxyphenyl)((4-vinylphenyl)amino)methyl)phenol (**4a**), 2-(phenyl((4-vinylphenyl)amino)methyl)phenol (**4b**) and 2-((4-chlorophenyl)((4-vinylphenyl)amino)methyl)phenol (**4c**) contained in the study were synthesized in the previous study. The geometrical optimization of these three monomers were done by HF,DFT / B3LYP and DFT/ WB97XD methods using 6-311 ++ G (d, p) set.

Determination of MEP surfaces; It is important in terms of providing information about interactions and chemical behaviours within the molecule.

When looked at Total Energy ranges, it was seen 4a compound have a high value, especially at B3LYP calculation. it can be said 4a compound containing an electron-donating group is prone to chemical reactions.

Table-1: Calculated Total Energy ranges for Alkylaminophenol compounds.

Compounds	HF	B3LYP	WB97XD
4a	-7.223 e-2 and 7.223 e-2	-6.511 e-2 and 6.511 e-2	-6.942 e-2 and 6.942 e-2
4b	-7.311 e-2 and 7.311 e-2	-6.668 e ⁻² and 6.668 e ⁻²	-7.041 e-2 and 7.041 e-2
4c	-7.539 e-2 and 7.539 e-2	-6.916 e ⁻² and 6.916 e ⁻²	-7.308 e ⁻² and 7.308 e ⁻²




Fig. 1: Synthesis, optimization(DFT/B3LYP/6-31++G(d,p)), molecular elektrostatic surfaces and contour maps of alkylaminophenol compounds.

NLO Analysis

Nonlinear optical properties of materials (NLO) plays an important role in the design of electronic structure. NLO properties of compound are originated from π electrons. Increased conjugation or inclusion of donor groups changes NLO properties. In general, quantum chemical calculations explain the relationship between the electronic structure and NLO properties. One of the compounds used for investigation of NLO properties of molecular systems is p-nitroaniline, thus p-nitroaniline was chosen for the reference compound in this work. NLO properties of alkylaminophenol compounds have never been studied in the literature before. Isotropic linear polarizability (α), anisotropic linear polarizability $\Delta\alpha$, first-order hyperpolarizability (β) and total dipole moment (μ) values were calculated by HF, DFT/B3LYP and DFT/WB97XD methods with 6-311++G(d,p) set.

As hyperpolarizability is difficult to measure directly, the computational calculation is an alternate choice. In the presence of an applied electric field, the energy of a system is a function of the electric field. The first hyperpolarizability is a third rank tensor that can be described by a $3 \times 3 \times 3$ matrix wherein the 27 components of the 3D matrix can be reduced to 10 components due to Kleinman symmetry [32-33]. The complete equation for calculating the magnitude of fundamental NLO parameters μ , α , $\Delta\alpha$ and β of the title molecule using the x, y, z components from Gaussian 09 output are as follows.

$$\mu = (\mu_x^2 + \mu_y^2 + \mu_z^2)^{1/2}$$

where μ_x , μ_y and μ_z are dipole moments along x, y and z directions

$$\langle\alpha\rangle = 1/3(\alpha_{xx} + \alpha_{yy} + \alpha_{zz})$$

where μ_{xx} , μ_{yy} , and μ_{zz} are the diagonal components of polarizability tensor.

$$\Delta\alpha = [1/2((\alpha_{xx}-\alpha_{yy})^2 + (\alpha_{yy}-\alpha_{zz})^2 + (\alpha_{zz}-\alpha_{xx})^2)]^{1/2}$$

$$\langle\beta\rangle = [(\beta_{xxx} + \beta_{xyy} + \beta_{xzz})^2 + (\beta_{yyy} + \beta_{xxy} + \beta_{yzz})^2 + (\beta_{zzz} + \beta_{xxz} + \beta_{yyz})^2]^{1/2}$$

NLO data of p-NA selected as standard with alkylaminophenols containing electron acceptors, donors and neutral substituents were shown in Table 2.

Looking at the NLO data; It is seen that 4c has a higher dipole moment than 4b and 4a. However, this value is lower than the dipole moment value of p-NA selected as standard. Linear polarizability values are negative, indicating that there is a dipole in the opposite direction of the electrical field. Linear polarizability values of selected alkylaminophenols are 2.5 times of p-NA. The sequence for linear polarizability can be written as $\alpha_{Cl} > \alpha_{MeO} > \alpha_H > \alpha_{p-NA}$. In anisotropic linear polarizability, this order is $\alpha_{MeO} > \alpha_{Cl} > \alpha_H > \alpha_{p-NA}$. When the first order hyperpolarizability values are examined, it is seen that the alkylaminophenols are approximate twice the hyperpolarizability value of p-NA. Here, the order is $\beta_{Cl} > \beta_H > \beta_{MeO} > \beta_{p-NA}$.

Table-2: NLO values of alkylaminophenol compounds.

	HF				B3LYP				WB97XD			
	p-NA	4a	4b	4c	p-NA	4a	4b	4c	p-NA	4a	4b	4c
μ_x	6.95	-1.91	-2.87	-0.92	-7.45	-2.59	-3.38	-1.55	7.04	-2.32	-3.23	-1.64
μ_y	0.00	-2.07	-1.95	-4.75	-0.00	-1.95	-1.84	-4.62	0.00	-1.88	-1.80	-4.57
μ_z	0.88	-0.83	0.42	0.47	0.69	-0.90	0.33	0.39	0.73	-0.79	0.36	0.47
μ	7.00	2.94	3.50	4.86	7.48	3.36	3.86	4.89	7.08	3.09	3.72	4.88
α_{xx}	-61.32	-152.74	-136.35	-154.37	-58.75	-155.60	-138.71	-156.33	-58.16	-151.25	-134.28	-150.50
α_{yy}	-52.82	-123.91	-121.69	-141.13	-53.28	-123.67	-121.96	-140.29	-52.42	18.07	-119.26	-137.56
α_{zz}	-61.00	-144.12	-132.34	-142.60	-60.62	-142.98	-131.20	-141.54	-60.32	-5.14	-131.29	-142.32
$\langle\alpha\rangle$	-8.65	-2.08	-1.93	-2.16	-8.52	-2.08	-1.94	-2.16	-8.44	-6.83	-1.9	-2.13
	$\times 10^{-24}$	$\times 10^{-23}$	$\times 10^{-23}$	$\times 10^{-23}$	$\times 10^{-24}$	$\times 10^{-23}$	$\times 10^{-23}$	$\times 10^{-23}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-23}$	$\times 10^{-23}$
$\Delta\alpha$	1.24	3.8	1.9	1.86	9.79	4.13	2.15	2.29	1.48	2.36	2.04	1.68
	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-25}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-24}$	$\times 10^{-23}$	$\times 10^{-24}$	$\times 10^{-24}$
β_{xxx}	89.08	-22.52	-35.12	1.37	-99.46	-44.53	-53.34	-22.70	94.67	-31.22	-48.40	-19.87
β_{xyy}	16.16	-60.58	-46.94	-6.07	16.70	-63.87	-45.51	-11.43	16.98	-54.93	-45.06	-11.73
β_{xzz}	-13.59	-9.55	-9.59	-12.89	13.00	-11.51	-13.47	-15.13	-13.23	-12.37	-10.01	-13.67
β_{yyy}	0.00	-37.34	-32.69	-144.55	-0.00	-27.86	-28.46	-132.43	0.00	-24.35	-30.61	-142.62
β_{xyx}	-0.00	-7.67	-42.78	-38.60	-0.00	-9.63	-39.76	-36.70	0.00	-18.44	-41.11	-34.77
β_{zzz}	0.00	0.71	-5.19	-1.75	0.00	-3.04	-7.08	-5.19	-0.00	1.51	-4.238	2.18
β_{zzx}	0.73	12.40	12.03	12.84	0.50	11.59	11.10	11.77	0.56	10.27	9.88	9.42
β_{zzz}	16.38	-36.90	-6.45	-20.02	12.91	-34.14	-6.07	-18.42	13.68	-26.603	-4.96	-16.38
β_{yyz}	0.49	0.953	18.70	33.38	0.42	1.22	19.53	33.46	0.44	-5.29	16.24	29.30
$\langle\beta\rangle$	8.06	9.1	1.08	1.62	8.99	1.09	1.18	1.58	8.60	9.42	1.12	1.58
	$\times 10^{-31}$	$\times 10^{-31}$	$\times 10^{-30}$	$\times 10^{-30}$	$\times 10^{-31}$	$\times 10^{-30}$	$\times 10^{-30}$	$\times 10^{-30}$	$\times 10^{-31}$	$\times 10^{-31}$	$\times 10^{-30}$	$\times 10^{-30}$

*GAUSSIAN-09W output are reported in atomic units (a.u.), the calculated values ($\langle\alpha\rangle$, $\Delta\alpha$, $\langle\beta\rangle$) have been converted into electrostatic units (esu) (α : 1 a.u. = 0.1482 $\times 10^{-24}$ esu; β : 1 a.u. = 8.6393 $\times 10^{-33}$ esu)


As a result, it can be said that the NLO properties of these alkylaminophenol compounds do not have high enough values[34]. However, it can contribute to the optical field with its values that cannot be ignored.

Frontier molecular orbitals (FMOs)

The molecular reactivity (FMO) of a molecule is important in defining its optical and electrical properties, and in defining the absorption of light. According to the molecular orbital theory; all molecules have HOMO (Highest occupied molecular

orbital) and LUMO (Lowest Unoccupied molecular orbital). The frontier molecular orbital (HOMO and LUMO) shapes of alkylaminophenol compounds were determined using HF and DFT/ B3LYP, WB97XD methods with 6-311++G(d,p) basis set. The HOMO and LUMO orbitals for this molecule are given in Figure 2.

Looking at Figure 2, it is seen that the alkylaminophenol containing the Meo substituent has higher energy value in all three methods. Thus, it is proved by the data that the reaction predisposition is $4a > 4b > 4c$.






Fig. 2: HOMO and LUMO orbitals of Alkylaminophenol compounds with the energy gap (HF/B3LYP/WB97XD).

Conclusion

In this study; For the first time, non-linear optical properties of three alkylaminophenol compounds were examined depended to substituents. Compared to p-NA, it was determined that the linear polarizability value was two and a half times higher, and the hyperpolarizability values were about two times higher. It was observed that the substituents in the alkylaminophenol structure had an effect on these values. Although these values are not high enough, it suggests that NLO properties will be strengthened with different substituents. In summary, we can say that alkylaminophenol compounds have an area of use outside of medical fields.

Acknowledgments

This study was supported with KUAP(F)-2016/5 project by Bursa Uludag University Scientific Research Projects Unit

References

1. R.Wang, J. Xu. Selective alkylation of aminophenols, *Arkivoc*, **ix**, 293 (2010).
2. Y.Ulaş, Experimental and Theoretical Studies of 2-(naphthalen-1-yl (piperidin-1-yl) methyl)phenol Compound, *J.Chem.Soc.Pak.* **42**, 818 (2020).
3. Í Neto, J. Andrade, A.S. Fernandes, R. Pinto, S. Catarina, K. Jagadish, A. Priimagi, R.N. Candeias, P. Rijo, Multicomponent Petasis-borono Mannich Preparation of Alkylaminophenols and Antimicrobial Activity Studies, *ChemMedChem.* **11**, 2015 (2016).
4. Y. Liu, L. Wang, Y. Sui, J. Yu, Solvent-free synthesis of alkylaminophenols via petasis Boronic Mannich reaction in one pot without catalysts, *Chinese J. Chem.* **28**, 2039 (2010).
5. P. Doan, T. Nguyen, O. Yli-Harja, M. Kandhavelu, O. Yli-Harja, P. Doan, T. Nguyen, O. Yli-Harja, N.R. Candeias, Effect of alkylaminophenols on growth inhibition and apoptosis of bone cancer cells, *Eur. J. Pharm.Sci.* **107**, 208 (2017).
6. N. Takahashi, T. Ohba, T. Yamauchib, K. Higashiyama, Antioxidant and anticancer activities of novel p- alkylaminophenols and p-acylaminophenols (aminophenol analogues), *Bioorganic & Medicinal Chemistry*, **14**6089 (2006).
7. P. Wu, M. Givskov, T.E. Nielsen, Reactivity and Synthetic Applications of Multicomponent Petasis Reactions, *Chem. Rev.* **119**, 11245 (2019).
8. N.R. Candeias, F. Montalbano, P.M.S.D. Cal, P.M.P. Gois, Boronic acids and esters in the petasis-borono mannich multicomponent reaction, *Chem. Rev.* **110**, 6169 (2010).
9. N.A. Petasis, I.A. Zavialov, A new and practical synthesis of α -amino acids from alkenyl boronic acids, *J. Am. Chem. Soc.* **119**, 445 (1997).
10. Y.M. Chang, S.H. Lee, M.H. Nam, M.Y. Cho, Y.S. Park, C.M. Yoon, Petasis reaction of activated quinoline and isoquinoline with various boronic acids, *Tetrahedron Lett.* **46**, 3053 (2005).
11. S. Noushini, M. Mahdavi, L. Firoozpour, S. Moghimi, A. Shafiee, A. Foroumadi, Efficient

- multicomponent synthesis of 1,4-benzodiazepine-3,5-diones: a Petasis-based approach, *Tetrahedron*, **71**, 6272 (2015).
12. D.E. Portlock, D. Naskar, L. West, M. Li, Petasis boronic acid-Mannich reactions of substituted hydrazines: Synthesis of α -hydrazinocarboxylic acids, *Tetrahedron Lett.* **43**, 6845 (2002).
 13. D. Naskar, A. Roy, W.L. Seibel, D.E. Portlock, Novel Petasis boronic acid-Mannich reactions with tertiary aromatic amines, *Tetrahedron Lett.* **44**, 5819 (2003).
 14. B. Kaboudin, A. Zangoeei, F. Kazemi, T. Yokomatsu, Catalyst-free Petasis-type reaction: Three-component decarboxylative coupling of boronic acids with proline and salicylaldehyde for the synthesis of alkylaminophenols, *Tetrahedron Lett.* **59**, 1046 (2018).
 15. D.Sajan, H. Joe, V.S.J ayakumar, J. Zaleski, Structural and electronic contributions to hyperpolarizability in methyl p-hydroxy benzoate, *Journal of Molecular Structure*, **785**, 43 (2006).
 16. B.J. Coe, J.A. Harris, L.A. Jones, B.S. Brunschwig, K. Song, K. Clays, J. Garin, J. Orduna, S.J. Coles, M.B. Hursthouse, Syntheses and Properties of Two-Dimensional Charged Nonlinear Optical Chromophores Incorporating Redox-Switchable cis-Tetraammineruthenium(II) Centers, *J. Am. Chem. Soc.*, **127**, 4845 (2005).
 17. G. de la Torre, P. Vazquez, F. Agullo-Lopez, T. Torres, Chem. Role of Structural Factors in the Nonlinear Optical Properties of Phthalocyanines and Related Compounds, *Chem. Rev.*, **104**, 3723 (2004).
 18. P. Vinothkumar, R. M. Kumar, R. Jayavel, A. Bhaskaran, Synthesis, growth, structural, optical, thermal and mechanical properties of an organic Urea maleic acid single crystals for nonlinear optical applications, *Optics & Laser Technology*, **81**, 145 (2016).
 19. A. Linda Varghese, I. Abraham, M. George, DFT Studies on Nonlinear Optical Properties of N [(Naphthalen-5-yl)methyl]-4-Nitrobenzamine, *Mater. Today Proc.* **9**, 92 (2019).
 20. S. Saravanan, V. Balachandran, Conformational stability, spectroscopic (FT-IR, FT-Raman and UV-Vis) analysis, NLO, NBO, FMO and Fukui function analysis of 4-hexylacetophenone by density functional theory, *Spectrochim. Acta - Part A Mol. Biomol. Spectrosc.* **138**, 406 (2015).
 21. R. Mathammal, N. Sudha, L. Guru Prasad, N. Ganga, V. Krishnakumar, Spectroscopic (FTIR, FT-Raman, UV and NMR) investigation and NLO, HOMO-LUMO, NBO analysis of 2-Benzylpyridine based on quantumchemical calculations, *Spectrochim. Acta - Part A Mol. Biomol. Spectrosc.* **137**, 740 (2015).
 22. S. Muthu, E. Elamurugu Porchelvi, M. Karabacak, A.M. Asiri, S.S. Swathi, Synthesis, structure, spectroscopic studies (FT-IR, FT-Raman and UV), normal coordinate, NBO and NLO analysis of salicylaldehyde p-chlorophenylthiosemicarbazone, *J. Mol. Struct.* **1081**, 400 (2015).
 23. R. Mathammal, K. Sangeetha, M. Sangeetha, R. Mekala, S. Gadheeja, Molecular structure, vibrational, UV, NMR, HOMO-LUMO, MEP, NLO, NBO analysis of 3,5 di tert butyl 4 hydroxy benzoic acid, *J. Mol. Struct.* **1120**, 1 (2016).
 24. S.M. Soliman, J. Albering, M.A.M. Abu-Youssef, Molecular structure, spectroscopic properties, NLO, HOMO-LUMO and NBO analyses of 6-hydroxy-3(2H)-pyridazinone, *Spectrochim. Acta - Part A Mol. Biomol. Spectrosc.* **136**, 1086 (2015).
 25. S. Guidara, H. Feki, Y. Abid, Structural, vibrational, NLO, MEP, NBO analysis and DFT calculation of bis 2,5-dimethylanilinium sulfate, *J. Mol. Struct.* **1080**, 176 (2015).
 26. L. Jensen, P.T. Van Duijnen, The first hyperpolarizability of p-nitroaniline in 1,4-dioxane: A quantummechanical/molecular mechanics study, *J. Chem. Phys.* **123**, 074307 (2005).
 27. S. F. López, M. P. Meza, F. T. Hoyos, Study of the nonlinear optical properties of 4-nitroaniline type compounds by density functional theory calculations: Towards new NLO materials, *Computational and Theoretical Chemistry*, **1133**, 25 (2018).
 28. S.A. Halim, M. A. Ibrahim, Synthesis, DFT calculations, electronic structure, electronic absorption spectra, natural bond orbital (NBO) and nonlinear optical (NLO) analysis of the novel 5-methyl-8H-benzo[h]chromeno[2,3-b][1,6] naphthyridine-6(5H),8-dione (MBCND), *Journal of Molecular Structure*, **1130**, 543 (2017).
 29. Y. Ulaş, Akıllı Malzemelerin Hazırlanmasında Kullanılacak Amin Türevi Monomerlerin Sentez ve Karakterizasyonu, *Eur. J. Sci. Technol.* **16**, 242 (2019).
 30. M.J. Frisch, G.W. Trucks, H.B. Schlegel, G.E. Scuseria, M.A. Robb, J.R. Cheeseman, G. Scalmani, V. Barone, B. Mennucci, G.A. Petersson, H. Nakatsuji, M. Caricato, X. Li, H.P. Hratchian, A.F. Izmaylov, J. Bloino, G. Zheng, J.L. Sonnenberg, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J. Hasegawa, M. Ishida, T. Nakajima,

- Y. Honda, O. Kitao, H. Nakai, T. Vreven, J.A. Montgomery Jr., J.E. Peralta, F. Ogliaro, M. Bearpark, J.J. Heyd, E. Brothers, K.N. Kudin, V.N. Staroverov, R. Kobayashi, J. Normand, K. Raghavachari, Rendell, J.C. Burant, S.S. Iyengar, J. Tomasi, M. Cossi, N. Rega, J.M. Millam, M. Klene, J.E. Knox, J.B. Cross, V. Bakken, C. Adamo, J. Jaramillo, R. Gomperts, R.E. Stratmann, O. Yazyev, A.J. Austin, R. Cammi, C. Pomelli, J.W. Ochterski, R.L. Martin, K. Morokuma, V.G. Zakrzewski, G.A. Voth, P. Salvador, J.J. Dannenberg, S. Dapprich, A.D. Daniels, Ö. Farkas, J.B. Foresman, J.V. Ortiz, J. Cioslowski, D.J. Fox, Gaussian 09, Revision C.01, Gaussian, Inc, Wallingford, CT, 2009.
31. GaussView, Version 5, in: Roy Dennington, Todd Keith, John Millam (Eds.), Semichem Inc., Shawnee Mission KS, 2009.
32. D. A. Kleinman, Nonlinear Dielectric Polarization in Optical Media, *Phys. Rev.*, **126**, 1977 (1962).
33. J. Karpagam, N. Sundaraganesan, S. Sebastian, S. Manoharan, M. Kurt, Molecular structure, vibrational spectroscopic, first-order hyperpolarizability and HOMO, LUMO studies of 3-hydroxy-2-naphthoic acid hydrazide, *Journal of Raman Spectroscopy*, **41**, 53 (2010).
34. H. Xu, F. Liu, D. L. Elder, L. E. Johnson, Y. Coene, K. Clays, B. H. Robinson, L.R. Dalton, *Chem. Mater.*, **32**, 1408 (2020).